

**SECTION 7.08  
DAMPPROOFING**

**7.08.01--Description:** Dampproofing of concrete or masonry work shall consist of a coating of asphalt as indicated on the plans and in accordance with these specifications.

**7.08.02--Materials:** The materials for this work shall conform to the requirements of Article M.12.05.

**7.08.03--Construction Methods:** The surface to which the dampproofing coating is to be applied shall be cleaned of all loose and foreign material and dirt and shall be dry. Where necessary, the Engineer may require the surface to be scrubbed with water and a stiff brush, after which the surface shall be allowed to dry before the application of the primer.

Concrete, brick or other surfaces which are to be protected by dampproofing shall be thoroughly clean and dry before the primer is applied. One coat of primer and one coat of sealer shall be applied using methods, application rates and temperature constraints as recommended by the Manufacturer of each product.

Care shall be taken to confine all applied material to the areas to be dampproofed and to prevent disfigurement of any other parts of the structure by dipping or spreading.

**7.08.04--Method of Measurement:** This work will be measured for payment by the number of square meters of dampproofing, consisting of primer and seal coat, completed and accepted within the neat lines shown on the plans or as ordered by the Engineer.

**7.08.05--Basis of Payment:** This work will be paid for at the contract unit price per square meter for "Dampproofing," complete in place, including all material, equipment, tools, labor and incidental expense.

Pay Item	Pay Unit
Dampproofing	m <sup>2</sup>