

**DIVISION III
MATERIALS SECTION**

**SECTION M.01
GRADATION OF AGGREGATE**

M.01.01--Gradation table for sizes of crushed or broken stone, crushed and uncrushed gravel and reclaimed miscellaneous aggregate.

PERCENT PASSING BY MASS NAME							
Square Mesh Sieves	No. 3	No. 4	No. 6	No. 67	No. 8	Screenings	Dust
63 mm	100						
50 mm	90-100	100					
37.5 mm	35-70	90-100					
25 mm	0-15	20-55	100	100			
19 mm		0-15	90-100	90-100			
12.5 mm	0-5		20-55		100		
9.5 mm		0-5	0-15	20-55	85-100	100	
4.75 mm			0-5	0-10	10-30		100
2.36 mm				0-5	0-10	60-100	40-100
1.18 mm					0-5		

Reclaimed miscellaneous aggregate shall only be used where authorized in the specifications.